



Mulcol International
 Arnesteinweg 18
 4338 PD Middleburg
 Netherlands

Eurofins Product Testing A/S
 Smedeskovvej 38
 DK-8464 Galten
 Denmark

Tel. +45 70 22 42 76
 Fax +45 70 22 42 75
 voc@eurofins.dk
 www.eurofins.com/product-emissions

Date
 14 February 2017

Your ref.
 -

Our ref.
 G13688ARev_03

Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

Sample material

Sample identification	Mulcol® Multimastic SP
Product type	Sealant
Product data, according to manufacturer	Density: 1.6 g/cm ^{3**} Water content: 0 g/l** Exempt compounds***
Date received	2 February 2012
Analytical period	February 2012

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %
Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The backing paper has been removed from the self-adhesive label material prior the testing.				

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, see also www.eurofins.dk, keyword: Måleusikkerhed

Analytical results

	Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
Mulcol® Multimastic SP	83	14 to 15**	0***	42 to 62	420*

* VOC limit for "Other Sealants".

** Given by the client.

*** No information about exempt compounds. Set to zero.

This amended report replaces the previous report. The water content has been added and the VOC limit has been corrected.

Eurofins Product Testing A/S

Morten Sielemann
 Analytical Chemist